

CertiMaC  
soc.cons. a r.l.  
Via Granarolo, 62  
48018 Faenza RA  
Italy  
tel. +39 0546 670363  
fax +39 0546 670399  
www.certimac.it  
info@certimac.it

R.I. RA,  
partita iva e  
codice fiscale  
02200460398  
R.E.A. RA  
180280  
capitale sociale  
€ 84.000  
interamente versato


# TEST REPORT

010118 - R - 4289

## ANNEX TO THE CERTIFICATE OF CONFORMITY 030/15

### Tests executed by

Ind. Tech. Germano Pederzoli



Ind. Tech. Federica Farina



### Drawn up

Dr. Marco Marsigli



### Approved

Eng. Luca Laghi



PLACE AND DATE OF ISSUE: Faenza, 04/02/2015

COMPANY: **F.B.M. – Fornaci Briziarelli Marsciano S.p.A.**

ADDRESS: Località Fornaci  
06055 Marsciano (PG)

TYPE OF PRODUCT: **Coppo Grande**  
(over and under tile)

STANDARD APPLIED: UNI EN 1304, UNI EN 1024, UNI EN 538,  
UNI EN 539-1, UNI EN 539-2

### DECLARED VALUES:

LENGTH 500 mm  
CAMBER 0.0 mm  
FIXING No

SAMPLING DATE: 12/10/2014

TESTS EXECUTED: February - March 2015


TESTS EXECUTED AT: CertiMaC, Faenza

CertiMaC  
soc. cons. a r.l.  
Via Granarolo, 62  
48018 Faenza RA  
Italia  
tel +39 0546 670363  
fax +39 0546 670399  
www.certimac.it  
info@certimac.it

R.I.RA,  
partita iva e  
codice fiscale  
02200460398  
R.E.A.RA  
180280  
capitale sociale  
€ 60.000  
interamente versato

**Tests executed by**

Ind. Tech. Germano Pederzoli



Ind. Tech. Federica Farina



**Drawn up**

Dr. Marco Marsigli



**Approved**

Eng. Luca Laghi



Test	N. specimens	Results	Acceptance limits
<b>Appearance and structure</b> N. unsatisfactory specimens	100	0	$\leq 5$
<b>Flexural strength</b> Minimum breaking load Average breaking load Maximum breaking load Standard deviation	10	5.91 kN 6.90 kN 7.88 kN 0.62 kN	$F \geq 1.00 \text{ kN}$
<b>Impermeability</b> Maximum impermeability Average impermeability  Category of impermeability	10	0.03 cm <sup>3</sup> cm <sup>2</sup> gg <sup>-1</sup> 0.02 cm <sup>3</sup> cm <sup>2</sup> gg <sup>-1</sup>  1	<u>Category 1</u> $IF \leq 0.60 \text{ cm}^3 \text{ cm}^2 \text{ gg}^{-1}$ $\bar{IF} \leq 0.50 \text{ cm}^3 \text{ cm}^2 \text{ gg}^{-1}$ <u>Category 2</u> $IF \leq 0.90 \text{ cm}^3 \text{ cm}^2 \text{ gg}^{-1}$ $\bar{IF} \leq 0.80 \text{ cm}^3 \text{ cm}^2 \text{ gg}^{-1}$
<b>Frost resistance, European single test method</b> Number of cycles carried out without defects  Level	6	150  Level 1	$\geq 150$ (Level 1) $\geq 90$ and $< 150$ (Level 2) $\geq 30$ and $< 90$ (Level 3)
<b>Individual dimensions: Length</b> Average tolerance Minimum tolerance Maximum tolerance	10	0.1 % 0.0 % 0.2 %	$L_T \leq \pm 2.0 \%$
<b>Camber</b> Average camber Minimum camber Maximum camber	10	0.1 % 0.0 % 0.3 %	$\bar{R}_L \leq 1.5 \%$
<b>Uniformity of transverse profile</b> Maximum difference between narrow ends Maximum difference between wide ends	10	5.0 mm 6.6 mm	$\Delta E_1 \leq 15.0 \text{ mm}$ $\Delta E_2 \leq 15.0 \text{ mm}$